

Form PTO-1390US DEPARTMENT OF COMMERCE PATENT AND TRADEMARK OFFICE
(Rev. 5-93)

**TRANSMITTAL LETTER TO THE UNITED STATES
DESIGNATED/ELECTED OFFICE (DO/EO/US)
CONCERNING A FILING UNDER 35 U.S.C. 371**

ATTORNEY'S DOCKET NO **H 3301 PCT/US**

U.S. APPLICATION NO. (if known sec. 17 CFR 1.5)

09/623115

INTERNATIONAL APPLICATION NO.
PCT/EP99/01049

INTERNATIONAL FILING DATE
February 17, 1999

PRIORITY DATE CLAIMED
February 26, 1998
February 9, 1999

TITLE OF INVENTION
FIBER-FREE SHAPED PARTS

APPLICANT(S) FOR DO/EO/US

Robert Graf, Maria-Elisabeth Kaiser, Klaus Lehr and Wolfgang Six

Applicant herewith submits to the United States Designated/Elected Office (EO/DO/US) the following items and other information:

1. ☒ This is a **FIRST** submission of items concerning a filing under 35 U.S.C. 371.
2. ☐ This a **SECOND** or **SUBSEQUENT** submission of items concerning a filing under 35 U.S.C. 371.
3. ☐ This express request to begin national examination procedures (35 U.S.C. 371(f)) at any time rather than delay examination until the expiration of the applicable time limit set in 35 U.S.C. 371(b) and PCT Articles 22 and 39 (1).
4. ☒ A proper Demand for International Preliminary Examination was made by the 19th month from the earliest claimed priority date.
5. ☒ A copy of the International Application as filed (35 U.S.C. 371(c)(2)).
 - a. ☐ is transmitted herewith (required only if not transmitted by the International Bureau).
 - b. ☒ has been transmitted by the International Bureau.
 - c. ☐ is not required, as the application was filed in the United States Receiving Office (RO/US).
6. ☒ A translation of the International Application into English (35 U.S.C. 371(c)(2)).
7. ☒ Amendments to the claims of the International Application under PCT Article 19 (35 U.S.C. 371(c)(3))
 - a. ☐ are transmitted herewith (required only if not transmitted by the International Bureau).
 - b. ☐ have been transmitted by the International Bureau.
 - c. ☐ have not been made; however, the time limit for making such amendments has NOT expired.
 - d. ☒ have not been made and will not be made.
8. ☐ A translation of the amendments to the claims under PCT Article 19 (35 U.S.C. 371(c)(3)).
9. ☒ An oath or declaration of the inventor(s) (35 U.S.C. 371(c)(4)). (UNEXECUTED)
10. ☐ A translation of the annexes to the International Preliminary Examination Report under PCT Article 36 (35 U.S.C. 371(c)(5)).

Items 11. to 16. below concern other document(s) or information included:

11. ☐ An Information Disclosure Statement under 37 CFR 1.97 and 1.98.
12. ☐ An assignment document for recording. A separate cover sheet in compliance with 37 CFR 3.28 and 3.31 is included.
13. ☒ A FIRST preliminary amendment
 - ☐ A SECOND or SUBSEQUENT preliminary amendment.
14. ☐ A substitute specification.
15. ☐ A change of power of attorney and/or address letter.
16. ☐ Other items or information.:

"Express Mail" mailing label number EL541612417US

U.S. Application No. (If known see CFR 1.30) 09/623115		INTERNATIONAL APPLICATION NO. PCT/EP99/01049		ATTORNEY'S DOCKET NUMBER H 3301 PCT/US	
17. ■ The following fees are submitted: Basic National Fee (37 CFR 1.492(a)(1)-(5)): Search Report has been prepared by the EPO or JPO..... \$840.00 International preliminary examination fee paid to USPTO (37CFR 1.482) \$670.00 No international preliminary examination fee paid to USPTO (37 CFR 1.482) but international search fee paid to USPTO (37CFR 1.445(a)(2)).... \$760.00 Neither international preliminary examination fee (37CFR 1.482) nor international search fee (37 CFR 1.445(a)(2)) paid to USPTO. \$970.00 International preliminary examination fee paid to USPTO (37CFR 1.482) and all claims satisfied provisions of PCT Article 33(2)-(4)..... \$96.00				CALCULATIONS PTO USE ONLY	
ENTER APPROPRIATE BASIC FEE AMOUNT				=	\$ 840 00
Surcharge of \$130.00 for furnishing the oath or declaration later than <input type="checkbox"/> 20 <input type="checkbox"/> 30 months from the earliest claimed priority date 37 (CFR 1.492(e)).				\$	
Claims	Number filed	Number Extra	Rate		
Total Claims	17 - 20 =	0	X 18.00	\$ 0	00
Independent Claims	2 - 3 =	0	X 78.00	\$ 0	00
Multiple dependent claims (s)(if applicable)		0	+ 260.00	\$ 0	00
TOTAL OF ABOVE CALCULATIONS				=	\$ 840 00
Reduction by 1/2 for filing by small entity, if applicable. Verified Small Entity statement must also be filed. (Note 37 CFR 1.9, 1.27, 1.28).				\$	
SUBTOTAL				=	\$ 840 00
Processing fee of \$130.00 for furnishing the English translation later the <input type="checkbox"/> 20 <input type="checkbox"/> 30 months from the earliest claimed priority date (37CFR 1.492(f)).....				\$	
TOTAL NATIONAL FEE				=	\$ 840 00
Fee for recording the enclosed assignment (37 CFR 1.21(h)). The assignment must be accompanied by an appropriate cover sheet (37 CFR 3.28, 3.31). \$40.00 per property +				\$	
TOTAL FEES ENCLOSED				=	\$ 840 00
				Amount to be: refunded	\$-----
				charged	840.00
a. <input type="checkbox"/> A check in the amount of \$_____ to cover the above fees is enclosed. b. ■ Please charge my Deposit Account No. <u>50-1177</u> in the amount of \$ 840.00 to cover the above fees. A triplicate copy of this sheet is enclosed. Order No. 00-0519 . c. ■ The Assistant Commissioner is hereby authorized to charge any additional fees which may be required, or credit any overpayment to Deposit Account No. <u>50-1177</u> . A triplicate copy of this sheet is enclosed. NOTE: Where an appropriate time limit under 37 CFR 1.494 or 1.495 has not been met, a petition to revive (37 CFR 1.137 (a) or (b)) must be filed and granted to restore the application to pending status.					
SEND ALL CORRESPONDENCE TO: Cognis Corporation, Law Dept. 2500 Renaissance Blvd., Ste. 200 Gulph Mills, PA 19406					
				SIGNATURE	
				Steven J. Trzaska NAME ATTORNEY FOR APPLICANT 36,296 REGISTRATION NUMBER	

"Express Mail" mailing label no. EL541612417US

09/623115
422 Rec'd PCT/PTO 25 AUG 2000
PATENT
Docket No. H 3301 PCT/US

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

RE: PCT/EP99/01049
International Filing Date: February 17, 1999
Priority Date Claimed: February 26, 1998
February 9, 1999
Applicant: Graf et al.
Title: FIBER-FREE SHAPED PARTS
Applicants' Reference: H 3301 PCT/US

PRELIMINARY AMENDMENT

Assistant Commissioner for Patents
Box PCT
Washington, DC 20231

ATTN: DO/EO/US

Sir:

Preliminary to examination, please amend the instant application as follows.

In the Specification:

At page 1, line 1, delete "Field of the Invention", and insert --Background of the Invention--.

At page 1, line 6, delete "Prior Art".

Enter a new page 21, submitted herewith, containing the Abstract of the Disclosure.

In the Claims:

Cancel claims 1-13, without prejudice.

Please enter the following new claims.

00623115
422 Rec'd PCT/PTO 25 AUG 2000

**Preliminary Amendment of U.S. National Stage for International Application
PCT/EP99/01049 filed February 17, 1999**

14. A fiber-free molding composition comprising:
- (a) a binder selected from the group consisting of an epoxide, a polyisocyanate, a furane-resin-free phenolic resin, and mixtures thereof; and
 - (b) a filler mixture containing:
 - (i) an inorganic high-temperature-resistant filler; and
 - (ii) a heat-activatable swelling agent.
15. The composition of claim 14 wherein the filler mixture further comprises:
- (iii) an adhesive;
 - (iv) a micropore-forming, high-temperature-resistant filler; and
 - (v) a grinding and/or anticaking agent.
16. The composition of claim 14 wherein the filler mixture has a pH of up to 7.5.
17. The composition of claim 15 wherein the filler mixture contains:
- (i) from 20 to 90% by weight of the inorganic high-temperature-resistant filler;
 - (ii) from 1 to 30% by weight of the heat-activatable swelling agent;
 - (iii) from 0.1 to 35% by weight of the adhesive;
 - (iv) from 2 to 40% by weight of the micropore-forming, high-temperature-resistant filler; and
 - (v) from 0.01 to 10% by weight of the grinding and/or anticaking agent, all weights being based on the total weight of the molding.
18. The composition of claim 14 further comprising a hardener.
19. The composition of claim 14 further comprising an emulsifier and a blowing

**Preliminary Amendment of U.S. National Stage for International Application
PCT/EP99/01049 filed February 17, 1999**

agent.

20. The composition of claim 14 wherein the molding has a density of from 100 to 300 kg/m³.

21. A process for making a fiber-free molding composition comprising:

(a) providing a binder selected from the group consisting of an epoxide, a polyisocyanate, a furane-resin-free phenolic resin, and mixtures thereof;

(b) providing a thermosetting hardener;

(c) providing a filler mixture containing:

(i) an inorganic high-temperature-resistant filler;

(ii) a heat-activatable swelling agent;

(iii) an adhesive;

(iv) a micropore-forming, high-temperature-resistant filler; and

(v) a grinding and/or anticaking agent; and

(d) combining (a)-(c) to form the fiber-free molding composition.

22. The process of claim 21 further comprising mixing an emulsifier with the binder.

23. The process of claim 21 further comprising providing a blowing agent.

24. The process of claim 21 wherein the filler mixture has a pH of up to 7.5.

25. The process of claim 21 further comprising introducing the molding mixture into a mold to form a solid, fiber-free foam form.

26. The product of the process of claim 21.

27. The product of the process of claim 22.


28. The product of the process of claim 23.

422 Rec'd PCT/PTO 2 5 AUG 2000

**Preliminary Amendment of U.S. National Stage for International Application
PCT/EP99/01049 filed February 17, 1999**

29. The product of the process of claim 24.
30. The product of the process of claim 25.

Respectfully submitted,



Steven J. Trzaska
(Reg. No. 36,296)
Attorney for Applicants
(610) 278-4929

Cognis Corporation
Law Department
2500 Renaissance Boulevard, Suite 200
Gulph Mills, PA 19406

SJT/mc
G:\Data\H3301pam.doc

422 Rec'd PCT/PTO 25 AUG 2000

Fiber-free Shaped PartsField of the Invention

This invention relates generally to flame-retardant materials and insulating materials and, more particularly, to fiber-free moldings containing binders and selected fillers.

5

Prior Art

Products containing mineral, ceramic and glass fibers are widely used in the field of heat and sound insulation. Large quantities of such materials - mostly in sheet or shell form - are also used for the preventive fire protection of buildings.

One of the advantages of these materials is their favorable thermal insulation capacity coupled with high mechanical strength. The materials in question are also distinguished by their easy machinability, low weight, high heat resistance and favorable self-burning behavior. Many of these "insulation materials" are classified as noninflammable building materials (Class A Building Materials according to DIN 4102, Part 1) or at least as flame-resistant building materials (Class B1 Building Materials according to DIN 4102, Part 1).

Mineral, ceramic and glass fibers are also known collectively as MMMF fibers. MMMF is the abbreviation for man-made mineral fibers. The toxicological effect of MMMF fibers is a contentious issue (see F.W. Löffler: **Aktuelle Aspekte zur Problematik der künstlichen Mineralfasern, Keramik und Glas 2, 14 (1996)**). Depending on their length-to-diameter ratio and their chemical composition, many of these fibers are classified as carcinogenic materials under the law on hazardous materials (see **Technische Regeln für Gefahrstoffe TRGS 905 and TRGS 906**). The absence of fibers is extremely important for factory

09/623115 "121900

hygiene and toxicological reasons because fibers are released both during processing of the moldings and also - through mechanical stressing - during their use (**VDI Kolloquium "Faserförmige Stäube", 9/93**).

Accordingly, there is an interest in MMMF-free products which have a similar property spectrum to the fiber-based materials mentioned above. Known MMMF-free materials are, for example, vermiculite, cellular concrete, perlite, calcium silicate and gypsum products. Thus, a highly filled phenolic resin foam is described, for example, in **DE-A1 3644468** (Isobloc Hüls). In this case, aluminium hydroxide and silicon oxide are used as fillers in quantities of more than 100% by weight, based on the phenolic resin. The result of this is that the rigid foams formed are correspondingly heavy (density 350 kg/m³). Another possibility is to use phenolic resins in combination with furane resins, as described in European patent application **EP-A2 0 325 935** (Rühl) and in **DE-C14227536** (Rühl), **DE-C1 3407512** (Rühl) and **DE-B1 2825295**. The products described therein use as fillers the main component aluminium hydroxide and added quantities of boric acid, sodium tetraborate and cryolite which are said to retard the burning rate of the organic foam matrix. The disadvantage of these products lies inter alia in the considerable outlay involved in avoiding odor emissions during production and in adjustment of the reactivity of the resin. None of the hitherto known materials represents an ideal replacement for the fiber-containing building materials because the properties of fiber-containing products cannot all be achieved.

Accordingly, the problem addressed by the present invention was to produce fiber-free moldings which would be comparable in their property spectrum with fiber-containing materials. In particular, the replacement materials would be comparable with the fiber-containing materials in their weight, their easy processability and their simple thermoformability under pressure. In addition, the materials according to the invention would show favorable self-burning behavior so that they could be used in the preventive

fire protection of buildings. Economic production would of course also be desirable.

Description of the Invention

5 The present invention relates to fiber-free moldings containing binders and fillers, characterized in that the binders are selected from the group of thermosets reacting out by addition of hardeners which consists of epoxides, polyisocyanates and furane-resin-free phenolic resins and in that solid mixtures of inorganic, high-temperature-resistant fillers and heat-
10 activatable swelling agents are present as fillers.

 The present invention also relates to fiber-free moldings containing binders and fillers, characterized in that adhesives, miropore-forming high-temperature-resistant fillers and grinding aids and/or anticaking agents are additionally present as fillers.

15 It has surprisingly been found that these moldings have the key positive properties of known fiber-containing moldings, such as low weight, easy machinability and thermoformability under pressure. In addition, these moldings show favorable self-burning behavior. Moreover, the factory hygiene requirements governing the handling of fiber-containing
20 moldings are not relevant, nor are the toxicological reservations concerning fiber-containing moldings. Products which can be processed surprisingly easily were obtained in particular in the case of fiber-free moldings which contain furane-resin-free phenolic resins as binders. In their case, controlled crosslinking of the binder and odor-free production are possible.
25 In addition, fiber-free moldings which can be produced at less cost for the same property spectrum are obtained.

Fillers

 In one preferred embodiment, the filler used is a solid mixture
30 consisting of

095315 "4900
005715 "4900

- 20 to 90% by weight of inorganic high-temperature-resistant fillers,
1 to 30% by weight of heat-activatable swelling agents,
0.1 to 35% by weight of adhesives,
2 to 40% by weight of micropore-forming high-temperature-resistant fillers,
5 0.01 to 10% by weight of grinding aids and/or anticaking agents,
with the proviso that the quantities add up to 100% by weight.

- In one particularly preferred embodiment, the filler used is a solid mixture consisting of
40 to 80% by weight of inorganic high-temperature-resistant fillers,
10 2 to 20% by weight of heat-activatable swelling agents,
1 to 25% by weight of adhesives,
2.5 to 30% by weight of micropore-forming high-temperature-resistant fillers,
0.1 to 5% by weight of grinding aids and/or anticaking agents,
15 with the proviso that the quantities add up to 100% by weight.

Inorganic high-temperature-resistant fillers

- Suitable inorganic high-temperature-resistant fillers are minerals such as, for example, calcium carbonate, calcium sulfate, clay, aluminium oxide, aluminium silicate, magnesium oxide, silica. Natural aluminium silicates, such as kaolin, mica, feldspar and mixtures thereof are preferred. These fillers are generally used in finely ground form, a mean particle size of 1 to 20 μm being particularly preferred. They are used in quantities of typically 20 to 90% by weight and preferably 40 to 80% by weight, based
25 on the total quantity of fillers.

Heat-activatable swelling agents

- The heat-activatable swelling agents used are substances or mixtures which undergo an increase in volume of 2 to 100 times and more
30 particularly 10 to 50 times at temperatures in the range from 100 to

1,000°C and more particularly at temperatures in the range from 200 to 900°C. This expansion compensates for the loss of volume occurring through the destruction of the binder at its decomposition temperature. Accordingly, the heat-activatable swelling agents make a key contribution to the integrity of the moldings at high temperatures. Such swelling agents are, for example, native vermiculite and perlite, expanded graphite, soda and potash waterglass. Other suitable heat-activatable swelling agents are mixtures of substances which are capable of releasing phosphoric acid and/or oligophosphoric acid and/or polyphosphoric acid and which consist of carbon-containing substances containing esterifiable hydroxyl groups and substances and mixtures which are capable of releasing a noninflammable gas at elevated temperature. The last-mentioned mixtures may also be used in microencapsulated form. Mixtures of swelling agents which develop their swelling effect at different temperatures are preferably used. This is the case, for example, with a mixture of vermiculite and perlite: whereas vermiculite expands at temperatures as low as 250 to 300°C, perlite only expands at 900 to 1,000°C. The swelling agents are normally used in a particle size of 0.0001 to 8 mm and preferably in a particle size of 0.0001 to 3 mm. The heat-activatable swelling agents are used in quantities of preferably 1 to 30% by weight and more preferably 2 to 20% by weight, based on the quantity of filler.

Micropore-forming high-temperature-resistant fillers

The micropore-forming high-temperature-resistant fillers are added to produce thermostable pores in the product in addition to the pores formed during foaming of the resin compound. This is particularly important because the pores formed during foaming of the resin compound have organic thermally decomposable cell walls which are destroyed at temperatures above the decomposition point of the binder. By contrast, the high-temperature-resistant fillers added are distinguished by the fact that

they form pores which are stable even at temperatures above the decomposition temperatures of the binder. Accordingly, they acquire the thermal insulatability of the moldings over broad temperature ranges up to ca. 1200°C. Suitable fillers are, for example, expanded perlite and
5 vermiculite, expanded clay, expanded graphite, hollow aluminium silicate, glass and/or fly ash beads, porous concrete and expanded waterglass. The micropore-forming high-temperature-resistant fillers may be used as individual substances although they are preferably used in the form of mixtures. They are used in a particle size of typically 0.0001 to 10 mm and
10 preferably 0.0001 to 2 mm. The micropore-forming high-temperature-resistant fillers are used in quantities of preferably 2 to 40% by weight and more preferably 2.5 to 30% by weight, based on the total quantity of fillers.

Adhesive

15 The adhesive used bonds both the inorganic heat-resistant fillers and the micropore-forming high-temperature-resistant fillers and the expandate of the heat-activatable swelling agents in the temperature ranges in which the binder no longer fulfils that function. Suitable adhesives are inorganic adhesives, more particularly high-temperature-
20 resistant inorganic adhesives. Adhesives suitable for the relevant temperature range (above the decomposition range of the binder) are, for example, glasses, such as soda-lime glasses, phosphates, borates and mixtures thereof. Suitable phosphates are both monophosphates and oligo- and polyphosphates, more particularly melamine phosphate,
25 melamine diphosphate, guanidine phosphate, monoammonium phosphate, diammonium phosphate, potassium triphosphate, sodium hexametaphosphate and ammonium polyphosphate. Preferred borates besides the borates of the alkali and alkaline earth metals are borates of zinc. It is preferred to use mixtures of these adhesives which develop their
30 effect over a broad temperature range. The adhesive is normally used in

finely ground form, i.e. in a particle size of 0.001 to 1,000 μm and preferably in a particle size of 0.001 to 100 μm , and in a quantity of preferably 0.1 to 35% by weight and more preferably 1 to 25% by weight, based on the total quantity of filler.

5

Grinding aids and/or anticaking agents

Grinding aids and/or anticaking agents are used for problem-free production, storage and incorporation of the fillers used. Suitable grinding aids and anticaking agents are, for example, highly disperse silicas, more particularly pyrogenic silicas. Pyrogenic silicas are highly disperse silicas which are obtained by flame hydrolysis. Apatites and stearates, more particularly calcium and aluminium stearates, may also be used. The advantage of using stearates is that they develop an adhesive effect at low temperatures. The grinding aids and/or anticaking agents are generally added to the mixtures in finely ground form during the grinding process and/or during the mixing process. They are used in a particle size of generally 0.001 to 200 μm and preferably 0.001 to 50 μm and in quantities of preferably 0.01 to 10% by weight and more preferably 0.1 to 5% by weight, based on the total quantity of fillers.

10
15
20

pH value

In one preferred embodiment, the aqueous suspension of the fillers has a pH value of or below 7.5. The advantage of this is that smaller quantities of acid can be used as hardener. The hardening process is thus quicker and more economical and the foam formed is improved in regard to cellularity, density and water content and also acid content (less residual acid in the end product).

25

The pH value of the fillers is determined on a 3.0% by weight aqueous suspension at 20°C.

30

Binders

The binders used are selected from the group of thermosets reacting out by addition of hardeners which consists of epoxides, polyisocyanates and furane-resin-free phenolic resins. It is particularly preferred to use
5 furane-resin-free phenolic resins.

The present invention includes the observation that, where furane-resin-free phenolic resins are used, fiber-free moldings distinguished by particularly easy processability and excellent self-burning behavior are obtained.

10 Phenolic resins is the collective name for synthetic resins obtained by condensation of phenols with aldehydes, more particularly formaldehyde, and modified reaction products which can be derived from the basic reaction mentioned above or are produced by addition of phenols onto unsaturated compounds. As described in **DIN 16916**, there are
15 various types of phenolic resins, such as unmodified phenolic resins, novolaks, resols, modified phenolic resins and phenol addition resins. In one particularly preferred embodiment of the invention, resols (synonym: phenol resol resins) are used.

The particularly preferred phenol resol resins used to produce the
20 moldings according to the invention are resins known per se which are obtained by alkaline condensation of phenol and formaldehyde. The condensation is controlled in known manner in such a way that foamable phenol resol resins are formed. A typical embodiment is characterized by the use of a liquid phenol resol resin which is obtained by condensation of
25 phenol with formaldehyde in a molar ratio of 1:1.35 to 1:1.9, preferably 1:1.4 to 1:1.7 and more preferably 1:1.5 using alkali metal and/or alkaline earth metals as catalysts. Alkali metals, especially aqueous sodium hydroxide solutions, are preferably used. The catalyst is used in a quantity of generally 0.7 to 1.5% by weight and preferably 0.9 to 1.3% by weight,
30 based on the phenol weighed in. The viscosity of the phenol resol resin is

generally in the range from 300 to 8,000 mPas and preferably in the range from 400 to 3,000 mPas, as determined with a Höppler falling ball viscosimeter at 20°C. The pH value is normally in the range from 7.0 to 9.0 and preferably in the range from 8.3 to 8.7. The resol resin is free from furane compounds.

The binder is used in quantities of preferably 20 to 80% by weight and more preferably 20 to 60% by weight.

Hardeners

Typical hardeners for the above-mentioned binders are amines, amidoamines, anhydrides, acids and polyols. Strong inorganic and/or organic acids are generally used to harden the phenolic resins preferably used. Acids normally used are hydrochloric acid, phosphoric acid, p-toluenesulfonic acid, xylenesulfonic acid and phenolsulfonic acid. The oxy acids of phosphorus and sulfur, such as phosphoric acid and sulfuric acid, are preferred. Sulfuric acid is particularly preferred. If the molding is intended to be halogen-free, this should be taken into account in the choice of the acid. The hardener is used in a quantity of generally 0.1 to 20% by weight and more particularly 0.5 to 12% by weight.

The present invention also relates to the fiber-free moldings claimed in claim 1 which contain emulsifiers and blowing agents as further components. In one preferred embodiment, the fiber-free moldings are obtained by reaction of

- 10 to 79.7% by weight of binder,
- 0.1 to 20% by weight of hardeners,
- 0.01 to 5% by weight of emulsifiers,
- 0.1 to 10% by weight of blowing agents,
- 20 to 70% by weight of fillers,

with the proviso that the quantities add up to 100% by weight.

In one particularly preferred embodiment, the fiber-free moldings are

obtained by reaction of
20 to 60% by weight of binder,
0.5 to 12% by weight of hardeners,
0.1 to 2% by weight of emulsifiers,
5 0.5 to 5% by weight of blowing agents,
25 to 50% by weight of fillers,
with the proviso that the quantities add up to 100% by weight.

The ratio by weight of resin to filler in the final molding can be
influenced by the choice of the quantities used, their water content and the
10 production process. In one particularly preferred embodiment, the fiber-
free moldings are characterized by a ratio by weight of resin to filler of 1:5.0
to 1:0.1, preferably 1:2.5 to 1:0.3, more preferably 1:2.0 to 1:0.5 and most
preferably 1:1.0 to 1:0.5.

15 Blowing agents

Suitable blowing agents are substances which give off gases under
the influence of the other mixture components, such as carbonates,
hydrogen carbonates and ammonium compounds. Low-boiling
hydrocarbons such as, for example, pentane, cyclopentane, acetone,
20 petroleum ether, methanol, hexane or mixtures of these hydrocarbons
which boil between 40 and 90°C are also suitable. Halogenated
hydrocarbons which boil in that temperature range may also be used as
blowing agents. These blowing agents may develop their blowing effect
either under the effect of an external heat source or under the effect of the
25 exothermic reaction of binder and hardener. Other suitable blowing agents
are microencapsulated acidic or alkaline liquids of which the membrane is
destroyed by mechanical or chemical action in the production process and
which then react with the fillers with evolution of gas. The blowing agents
are used in quantities of generally 0.1 to 10% by weight and preferably 0.5
30 to 5% by weight.

Emulsifiers

The emulsifier is needed to enable nonpolar blowing agents used and the fillers to be uniformly incorporated in the binder. Suitable emulsifiers are ionic, nonionic or amphoteric compounds which enable the blowing agents to be finely dispersed and/or the fillers to be completely wetted and hence more quickly incorporated. Alkyl polyglycosides and fatty acid derivatives, such as fatty acid amides, fatty acid imides, fatty acid amidoalkyl betaines and/or fatty acid ethoxylates and fatty acid propoxylates, are preferred. It is particularly preferred to use fatty acid ethoxylates, such as oleic acid ethoxylates or castor oil ethoxylates with 2 to 20 moles ethylene oxide. The use of castor oil ethoxylates with 15 to 20 moles of ethylene oxide is most particularly preferred. In another embodiment, ether sulfates are used as emulsifiers, fatty acid ether sulfates - especially sodium lauryl ether sulfate - being particularly preferred. The emulsifiers may be used both individually and in the form of mixtures in quantities of normally 0.01 to 5% by weight and preferably 0.1 to 2% by weight.

Production

The foaming of the binder with the filler is carried out in known manner. To this end, the binder is thoroughly mixed with the emulsifier. The filler mixture is then added. The blowing agent and then the hardener are added with intensive stirring. The individual components have to be carefully mixed to obtain a uniform foam (with no voids). After the hardener has been incorporated, the resin compound is transferred to a foaming mold. This foaming mold is generally heated, normally to temperatures of 40 to 60°C. The hardening time depends on the geometry of the mold, the reactivity of the resin used, the acid used and the quantity and properties of the fillers and on the mold temperature. Typical foam forms are panels although other forms (blocks, pipe sheaths, half-shells, etc.) may also be

used.

Density

5 The present invention also relates to the density of the fiber-free moldings which is generally in the range from 100 to 300 kg/m³, preferably in the range from 150 to 220 kg/m³ and more preferably in the range from 180 to 200 kg/m³.

10 Another advantage of the present invention is the interplay between binder - particularly the phenolic resin - and adhesive. Whereas the binder provides for the stability of the moldings at temperatures below the decomposition point of the binder, the adhesive is responsible for that function at temperatures above the decomposition point of the binder. In one preferred embodiment, the heat-activatable high-temperature-resistant swelling agents and the micropore-forming high-temperature-resistant fillers additionally provide for stability at those temperatures. The stability and/or integrity of the moldings over a broad temperature range is thus guaranteed.

The present invention also relates to the use of the fiber-free moldings as fire retardant and/or insulating moldings.

20 The present invention also relates to the use of the fiber-free moldings as composites. Possible composite materials are, for example, wood, metal and/or plastics. Typical forms, for example sheets, shells, half-pipes, etc., are again possible.

25 Commercial Applications

The fiber-free moldings according to the invention are at least equivalent in their properties to known fiber-containing moldings. Particular advantages are their easy machinability and thermoformability under pressure. In addition, the factory hygiene requirements governing the handling of fiber-containing moldings are not relevant, nor are the

30

toxicological reservations concerning fiber-containing moldings. Fiber-containing moldings can thus be replaced in virtually all fields of application. The fiber-free moldings according to the invention are particularly suitable for the production of fire-retardant moldings and
5 insulating moldings. They can be produced in any shapes known per se, such as sheets, shells, half-pipes, etc.

Examples

Example 1a

10 52% by weight of a phenol resol resin (molar ratio of phenol to formaldehyde 1:1.5; catalyst: 0.95% by weight aqueous sodium hydroxide solution, based on the phenol weighed in, 1,800-2,000 mPas) with a dry matter content of 75% by weight were introduced into a stirred vessel. 0.8% by weight of a sodium lauryl ether sulfate was added with stirring.
15 After homogenization, 36% by weight of a filler mixture (see Table 1) were gradually added with stirring so that a viscous resin compound was formed. 1.5% by weight of pentane were added to this resin compound with continued intensive mixing. Finally, after complete homogenization, 9.7% by weight of a 45% by weight aqueous sulfuric acid solution were added.
20 The homogenized mixture was poured into a steel mold preheated to 60°C, the quantity of compound weighed in relative to the volume of the mold being selected so that the end product had a density of 180 kg/m³. After the compound had been introduced, the mold was closed. The reaction time of the mixture was about 4 hours. After cooling of the mold, the
25 hardened foam block was removed and cut into shaped pieces.

Example 1b

Example 1a was repeated using the following phenol resol resin: molar ratio of phenol to formaldehyde 1:1.4; catalyst 1.1% by weight
30 aqueous sodium hydroxide solution, 7,400 mPas.

Example 1c

Example 1a was repeated using the following phenol resol resin: molar ratio of phenol to formaldehyde 1:1.6; catalyst 1.3% by weight aqueous sodium hydroxide solution, 5,500 mPas.

Example 1d

Example 1a was repeated using the following phenol resol resin: molar ratio of phenol to formaldehyde 1:1.7; catalyst 1.1% by weight aqueous sodium hydroxide solution, 500 mPas.

Table 1: filler mixture for Examples 1a, 1b, 1c and 1d

Function	Component	% by weight ¹	Mean particle size [µm]
Inorganic high-temperature-resistant filler	Kaolin	75.4	3
Heat-activatable swelling agent	Native vermiculite	9.8	0.001-3000
Adhesive	Melamine phosphate	2.4	20
	Zinc borate	2.4	5
Micropore former	Hollow glass beads	9.8	0.001-100
High-temperature resistant filler			
Grinding aid and/or anticaking agent	Calcium stearate	0.2	10

¹ Quantities in % by weight, based on total quantity of filler

Example 2a

58% by weight of a phenol resol resin (molar ratio of phenol to formaldehyde 1:1.5; catalyst: 0.95% by weight aqueous sodium hydroxide solution, based on the phenol weighed in, 1,800-2,000 mPas) with a dry

matter content of 70% by weight were introduced into a stirred vessel. 0.6% by weight of a castor oil ethoxylate + 20 moles ethylene oxide were added with stirring. After homogenization, 32% by weight of a filler mixture (see Table 2) were gradually added with stirring so that a viscous resin compound was formed. 1.8% by weight of pentane were added to this resin compound with continued intensive mixing. Finally, after complete homogenization, 7.6% by weight of a 50% by weight aqueous sulfuric acid solution were added. The homogenized mixture was poured into a steel mold preheated to 55°C, the quantity of compound weighed in relative to the volume of the mold being selected so that the end product had a density of 200 kg/m³. After the compound had been introduced, the mold was closed. After a reaction time of 5 hours and subsequent cooling of the mold, the hardened foam block was removed and cut into shaped pieces.

15 Example 2b

Example 2a was repeated using the following phenol resol resin: molar ratio of phenol to formaldehyde 1:1.4; catalyst 1.1% by weight aqueous sodium hydroxide solution, 7,400 mPas.

20 Example 2c

Example 2a was repeated using the following phenol resol resin: molar ratio of phenol to formaldehyde 1:1.6; catalyst 1.3% by weight aqueous sodium hydroxide solution, 5,500 mPas.

25 Example 2d

Example 2a was repeated using the following phenol resol resin: molar ratio of phenol to formaldehyde 1:1.7; catalyst 1.1% by weight aqueous sodium hydroxide solution, 500 mPas.

Table 2: filler mixture for Examples 2a, 2b, 2c and 2d

Function	Component	% by weight ¹	Mean particle size [μm]
Inorganic high-temperature-resistant filler	Kaolin	40	3
	Mica	30	0-50
Heat-activatable swelling agent	Expanded graphite	8.8	0-2000
	Native vermiculite	1.5	0-3000
	Native perlite	1.5	0-3000
Adhesive	Melamine phosphate	3.0	0-100
	Ammonium polyphosphate	3.0	0-100
Micropore former	Expanded perlite	6.0	0-3000
High-temperature resistant filler	Expanded vermiculite	3.0	0-4000
	Hollow fly ash beads	3.0	0-1000
Grinding aid and/or anticaking agent	Pyrogenic silica	0.2	0-50

¹ Quantities in % by weight, based on total quantity of filler

Example 3a

54.8% by weight of a phenol resol resin (molar ratio of phenol to formaldehyde 1:1.5; catalyst: 0.95% by weight aqueous sodium hydroxide solution, based on the phenol weighed in, 1,800-2,000 mPas) with a dry matter content of 70% by weight were introduced into a stirred vessel. 0.6% by weight of a castor oil ethoxylate + 20 moles ethylene oxide were added with stirring. After homogenization, 36.2% by weight of a filler mixture (see Table 3) were gradually added with stirring so that a viscous resin compound was formed. 1.2% by weight of pentane were added to this resin compound with continued intensive mixing. Finally, after

complete homogenization, 7.2% by weight of a 50% by weight aqueous sulfuric acid solution were added. The homogenized mixture was poured into a steel mold preheated to 55°C, the quantity of compound weighed in relative to the volume of the mold being selected so that the end product had a density of 200 kg/m³. After the compound had been introduced, the mold was closed. After a reaction time of 5 hours and subsequent cooling of the mold, the hardened foam block was removed and cut into shaped pieces.

Example 3b

Example 3a was repeated using the following phenol resol resin: molar ratio of phenol to formaldehyde 1:1.4; catalyst 1.1% by weight aqueous sodium hydroxide solution, 7,400 mPas.

Example 3c

Example 3a was repeated using the following phenol resol resin: molar ratio of phenol to formaldehyde 1:1.6; catalyst 1.3% by weight aqueous sodium hydroxide solution, 5,500 mPas.

Example 3d

Example 3a was repeated using the following phenol resol resin: molar ratio of phenol to formaldehyde 1:1.7; catalyst 1.1% by weight aqueous sodium hydroxide solution, 500 mPas.

Assuming that the average water content in the resin is 13.0%, the ratio by weight of resin to filler for the moldings obtained in accordance with Examples 3a to d is 1:0.8.

Table 3: filler mixture for Examples 3a, 3b, 3c and 3d

Function	Component	% by weight ¹	Mean particle size [µm]
Inorganic high-temperature-resistant filler	Kaolin	75.4	3
Heat-activatable swelling agent	Expanded graphite	9.7	0.001-2000
Adhesive	Ammonium polyphosphate	5.0	0.001-100
Micropore former	Hollow aluminium silicate beads	9.4	0.001-2000
High-temperature resistant filler			
Grinding aid and/or anticaking agent	Precipitated silica	0.5	0.001-50

¹ Quantities in % by weight, based on total quantity of filler

Fire-retardant properties and machinability

6 cm thick panels were cut from the foam blocks of Examples 1, 2 and 3 (a to d) and subjected to a small-scale burning test to DIN 4012. Fire resistance of more than 90 minutes was obtained in every case. The panels combined good mechanical strength with easy machinability with cutting tools.

CLAIMS

1. Fiber-free moldings containing binders and fillers, characterized in that the binders are selected from the group of thermosets reacting out by addition of hardeners which consists of epoxides, polyisocyanates and
5 furane-resin-free phenolic resins and in that solid mixtures of inorganic, high-temperature-resistant fillers and heat-activatable swelling agents are present as fillers.
2. Fiber-free moldings as claimed in claim 1, characterized in that adhesives, micropore-forming high-temperature-resistant fillers and
10 grinding aids and/or anticaking agents are additionally present as fillers.
3. Fibre-free moldings as claimed in claims 1 and 2, characterized in that an aqueous suspension of the fillers has a pH of or below 7.5.
4. Fiber-free moldings as claimed in claims 1 to 3, characterized in that the filler is a solid mixture consisting of
15 20 to 90% by weight of inorganic high-temperature-resistant fillers,
1 to 30% by weight of heat-activatable swelling agents,
0.1 to 35% by weight of adhesives,
2 to 40% by weight of micropore-forming high-temperature-resistant fillers
and
20 0.01 to 10% by weight of grinding aids and/or anticaking agents,
with the proviso that the quantities add up to 100% by weight.
5. Fiber-free moldings as claimed in claims 1 to 4, characterized in that they contain hardener as another component.
6. Fiber-free moldings as claimed in claims 1 to 5, characterized in that
25 they contain emulsifiers and blowing agents as further components.
7. Fiber-free moldings as claimed in claims 1 to 6, characterized in that they are obtained by reaction of
10 to 79.7% by weight of binder,
0.1 to 20% by weight of hardeners,
30 0.01 to 5% by weight of emulsifiers,

0.1 to 10% by weight of blowing agents,
20 to 70% by weight of fillers,
with the proviso that the quantities add up to 100% by weight.

8. Fiber-free moldings as claimed in claims 1 to 7, characterized in that
5 they contain furane-resin-free phenolic resins as binders.

9. Fiber-free moldings as claimed in claims 1 to 8, characterized in that
they contain furane-resin-free phenol resol resins as binders.

10. Fiber-free moldings as claimed in claims 1 to 9, characterized in that
they have a density of 100 to 300 kg/m³.

10 11. The use of the fibre-free moldings claimed in claims 1 to 10 for the
production of fire-retardant moldings.

12. The use of the fibre-free moldings claimed in claims 1 to 10 for the
production of insulating moldings.

13. The use of the fibre-free moldings claimed in claims 1 to 10 for the
15 production of composite materials.

Abstract of the Disclosure

A fiber-free molding composition containing: (a) a binder selected from the group consisting of an epoxide, a polyisocyanate, a furane-resin-free phenolic resin, and mixtures thereof; and (b) a filler mixture containing: (i) an inorganic high-temperature-resistant filler; and (ii) a heat-activatable swelling agent.

"Express Mail" mailing label number EL541612417US

PTO/SB/01 (6-95)

Approved for use through: 10/31/98 OMB 0651-0032

Type a plus sign (+) inside this box → ☐

Patent and Trademark Office; U.S. DEPARTMENT OF COMMERCE

0010/PTO Rev. 6/95 U.S. Department of Commerce Patent and Trademark Office DECLARATION FOR UTILITY OR DESIGN PATENT APPLICATION <input type="checkbox"/> Declaration Submitted with Initial Filing OR <input checked="" type="checkbox"/> Declaration Submitted after Initial Filing	Attorney Docket Number	H 3301 PCT/US
	First Named Inventor	Graf, Robert
	COMPLETE IF KNOWN	
	Application Number	
	Filing Date	
	Group Art Unit	
	Examiner Name	

As a below named inventor, I hereby declare that.

My residence, post office address, and citizenship are as stated below next to my name.

I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled:

FIBER-FREE SHAPED PARTS

(Title of the invention)

the specification of which

☐ is attached hereto

OR

☒ was filed on (MM/DD/YYYY) **02/17/1999** as United States Application Number or PCT International

Application Number **PCT/EP99/01049** and was amended on (MM/DD/YYYY) (if applicable).

I hereby state that I have reviewed and understand the contents of the above identified specification, including the claims, as amended by any amendment specifically referred to above.

I acknowledge the duty to disclose information which is material to patentability as defined in Title 37 Code of Federal Regulations, § 1.56.

I hereby claim foreign priority benefits under Title 35, United States Code §119(a)-(d) or §365(b) of any foreign application(s) for patent or inventor's certificate, or §365(a) of any PCT International application which designated at least one country other than the United States of America, listed below and have also identified below, by checking the box, any foreign application for patent or inventor's certificate, or of any PCT International application having a filing date before that of the application on which priority is claimed.

Prior Foreign Application Number(s)	Country	Foreign Filing Date (MM/DD/YYYY)	Priority Not Claimed	Certified Copy Attached?	
				YES	NO
198 08 131.6 199 05 153.4	Germany Germany	02/26/1998 02/09/1999	<input type="checkbox"/> <input type="checkbox"/> <input type="checkbox"/> <input type="checkbox"/> <input type="checkbox"/>	<input type="checkbox"/>	<input checked="" type="checkbox"/>
				<input type="checkbox"/>	<input checked="" type="checkbox"/>
				<input type="checkbox"/>	<input type="checkbox"/>
				<input type="checkbox"/>	<input type="checkbox"/>
				<input type="checkbox"/>	<input type="checkbox"/>

☐ Additional foreign application numbers are listed on a supplemental priority sheet attached hereto:

I hereby claim the benefit under Title 35, United States Code §119(e) of any United States provisional application(s) listed below.

Application Number(s)	Filing Date (MM/DD/YYYY)	<input type="checkbox"/> Additional provisional application numbers are listed on a supplemental priority sheet attached hereto.

Burden Hour Statement: This form is estimated to take .4 hours to complete. Time will vary depending upon the needs of the individual case. Any comments on the amount of time you are required to complete this form should be sent to the Chief Information Officer, Patent and Trademark Office, Washington, DC 20231. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO: Assistant Commissioner for Patents, Washington DC 20231.

**"Express Mail Post Office
to Addressee" service
Mailing Label Number**

EL541613616 US

Type a plus sign (+) inside this box → ☐

H 3301 PCT/US

DECLARATION**Page 2**

I hereby claim the benefit under Title 35, United States Code §120 of any United States application(s), or §365© of any PCT international application designating the United States of America, listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States or PCT international application in the manner provided by the first paragraph of Title 35, United States Code §112.1 acknowledge the duty to disclose information which is material to patentability as defined in Title 37, Code of Federal Regulations §1.56 which became available between the filing date of the prior application and the national or PCT international filing date of this application.

U.S. Parent Application Number	PCT Parent Number	Parent Filing Date (MM/DD/YYYY)	Parent Patent Number (if applicable)

☐ Additional U.S. or PCT international application numbers are listed on a supplemental priority sheet attached hereto.

As a named inventor, I hereby appoint the following attorney(s) and/or agent(s) to prosecute this application and to transact all business in the Patent and Trademark Office connected therewith:

☐ Firm Name Customer Number or label
OR
☒ List Attorney(s) and/or agent(s) name and registration number below:

Name	Registration Number	Name	Registration Number
John E. Drach	32,891	Aaron R. Ettelman	42,516
Steven J. Trzaska	36,296	Henry E. Millson, Jr.	18,980


☐ Additional attorney(s) and/or agent(s) named on a supplemental sheet attached hereto

Please direct all correspondence to: ☒ Customer Number or label **23657** OR ☒ Fill in correspondence address below

Name **Steven J. Trzaska**
Address
Address
City State Zip
Country Telephone **610-278-4929** Fax **610-278-6548**

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

Name of Sole or First Inventor: ☐ A petition has been filed for this unsigned inventor

Given Name **Robert** Middle Initial Family Name **Graf** Suffix e.g. Jr.
Inventor's Signature  Date **Dec. 04, 00**
Residence: City **Osterberg** State Country **Germany** Citizenship **Germany**
Post Office Address **Enzianweg 5**
Post Office Address
City **89296 Osterberg** State Zip Country **Germany** Applicant Authority

☒ Additional inventors are being named on supplemental sheet(s) attached hereto


Type a plus sign (+) inside this box → ☐

H 3301 PCT/US

DECLARATION				ADDITIONAL INVENTOR(S) Supplemental Sheet			
Name of Additional Joint Inventor, if any:				<input type="checkbox"/> A petition has been filed for this unsigned inventor			
Given Name	Maria-Elisabeth	Middle Initial		Family Name	Kaiser	Suffix e.g. Jr.	
Inventor's Signature	<i>Maria Kaiser</i>			Date	Dec. 04, 00		
Residence: City	Ulm	State		Country	Germany	Citizenship	Germany
Post Office Address	Friedrichshafener Strasse 93						
Post Office Address							
City	89079 Ulm	State		Zip		Country	Germany
						Applicant Authority	
Name of Additional Joint Inventor, if any:				<input type="checkbox"/> A petition has been filed for this unsigned inventor			
Given Name	Klaus	Middle Initial		Family Name	Lehr	Suffix e.g. Jr.	
Inventor's Signature				Date			
Residence: City	Linngenfeld	State		Country	Germany	Citizenship	Germany
Post Office Address	Neustadter Strasse 150						
Post Office Address							
City	67360 Linngenfeld	State		Zip		Country	Germany
						Applicant Authority	
Name of Additional Joint Inventor, if any:				<input type="checkbox"/> A petition has been filed for this unsigned inventor			
Given Name	Wolfgang	Middle Initial		Family Name	Six	Suffix e.g. Jr.	
Inventor's Signature				Date			
Residence: City	Frankfurt a. Main	State		Country	Germany	Citizenship	Germany
Post Office Address	Schenkendorfstrasse 17						
Post Office Address							
City	60431 Frankfurt a. Main	State		Zip		Country	Germany
						Applicant Authority	
Name of Additional Joint Inventor, if any:				<input type="checkbox"/> A petition has been filed for this unsigned inventor			
Given Name		Middle Initial		Family Name		Suffix e.g. Jr.	
Inventor's Signature				Date			
Residence: City		State		Country		Citizenship	
Post Office Address							
City		State		Zip		Country	
						Applicant Authority	
<input type="checkbox"/> Additional inventors are being named on supplemental sheet(s) attached hereto							

Type a plus sign (+) inside this box → ☐

H 3301 PCT/US

DECLARATION										ADDITIONAL INVENTOR(S) Supplemental Sheet					
Name of Additional Joint Inventor, if any:										<input type="checkbox"/> A petition has been filed for this unsigned inventor					
Given Name	Maria-Elisabeth			Middle Initial		Family Name	Kaiser			Suffix e.g. Jr.					
Inventor's Signature									Date						
Residence: City	Ulm			State		Country	Germany			Citizenship	Germany				
Post Office Address	Friedrichshafener Strasse 93														
Post Office Address															
City	89079 Ulm			State		Zip		Country	Germany			Applicant Authority			
Name of Additional Joint Inventor, if any:										<input type="checkbox"/> A petition has been filed for this unsigned inventor					
Given Name	Klaus			Middle Initial		Family Name	Lehr			Suffix e.g. Jr.					
Inventor's Signature									Date	Dec. 04, 00					
Residence: City	Linngenfeld			State		Country	Germany			Citizenship	Germany				
Post Office Address	Neustadter Strasse 150										DEX				
Post Office Address															
City	67360 Linngenfeld			State		Zip		Country	Germany			Applicant Authority			
Name of Additional Joint Inventor, if any:										<input type="checkbox"/> A petition has been filed for this unsigned inventor					
Given Name	Wolfgang			Middle Initial		Family Name	Six			Suffix e.g. Jr.					
Inventor's Signature									Date						
Residence: City	Frankfurt a. Main			State		Country	Germany			Citizenship	Germany				
Post Office Address	Schenkendorfstrasse 17														
Post Office Address															
City	60431 Frankfurt a. Main			State		Zip		Country	Germany			Applicant Authority			
Name of Additional Joint Inventor, if any:										<input type="checkbox"/> A petition has been filed for this unsigned inventor					
Given Name				Middle Initial		Family Name				Suffix e.g. Jr.					
Inventor's Signature									Date						
Residence: City				State		Country				Citizenship					
Post Office Address															
City				State		Zip		Country				Applicant Authority			
<input type="checkbox"/> Additional inventors are being named on supplemental sheet(s) attached hereto															

Type a plus sign (+) inside this box → ☐

H 3301 PCT/US

DECLARATION				ADDITIONAL INVENTOR(S) Supplemental Sheet			
Name of Additional Joint Inventor, if any:				<input type="checkbox"/> A petition has been filed for this unsigned inventor			
Given Name	Maria-Elisabeth	Middle Initial		Family Name	Kaiser	Suffix e.g. Jr.	
Inventor's Signature					Date		
Residence: City	Ulm	State		Country	Germany	Citizenship	Germany
Post Office Address	Friedrichshafener Strasse 93						
Post Office Address							
City	89079 Ulm	State		Zip		Country	Germany
						Applicant Authority	
Name of Additional Joint Inventor, if any:				<input type="checkbox"/> A petition has been filed for this unsigned inventor			
Given Name	Klaus	Middle Initial		Family Name	Lehr	Suffix e.g. Jr.	
Inventor's Signature					Date		
Residence: City	Linngenfeld	State		Country	Germany	Citizenship	Germany
Post Office Address	Neustadter Strasse 150						
Post Office Address							
City	67360 Linngenfeld	State		Zip		Country	Germany
						Applicant Authority	
Name of Additional Joint Inventor, if any:				<input type="checkbox"/> A petition has been filed for this unsigned inventor			
Given Name	Wolfgang	Middle Initial		Family Name	Six	Suffix e.g. Jr.	
Inventor's Signature	Wolfgang Six				Date	Dec. 09, 00	
Residence: City	Frankfurt a. Main	State		Country	Germany	Citizenship	Germany
Post Office Address	Schenkendorfstrasse 17						
Post Office Address							
City	60431 Frankfurt a. Main	State		Zip		Country	Germany
						Applicant Authority	
Name of Additional Joint Inventor, if any:				<input type="checkbox"/> A petition has been filed for this unsigned inventor			
Given Name		Middle Initial		Family Name		Suffix e.g. Jr.	
Inventor's Signature					Date		
Residence: City		State		Country		Citizenship	
Post Office Address							
Post Office Address							
City		State		Zip		Country	
						Applicant Authority	
<input type="checkbox"/> Additional inventors are being named on supplemental sheet(s) attached hereto							